





FEATURES

ARTICLE: MOSAIC				IN-01222/2011-4 IN-01558/2010-07 IN-01440-2010	
COMPOSITION: 48%PP 33%PES 19%CO					
WIDTH: 140	+4cm.	WEIGHT: 490	gr/m². +5%	686	gr/ml.+5%
STATISTICAL NUMBER: 54079300				WARP	WEFT
SEAM SLIPPAGE RESISTANCE (mm) EN ISO 13936/2:2004; Load Method(180 N) Seam Slippage (mm)				2	1.7
ABRASION RESISTANCE (End point) EN ISO 12947-2:1998				30.000	
ABRASION RESISTANCE (Change of aspect: 3000 ciclos) EN ISO 12947/4:1998 and EN 14465:2003 (Annex A) Colour Degradation on grey scale (From de 1 worst to 5 best)				4	
PILLING RESISTANCE EN ISO 12945/2:2000; Modified Martindale Method (2000 and 7000 cycles) Pilling index (From 1 worst to 5 best)				5	
ASSESSMENT OF IGNITABILITY EN 1021-1:2006 (cigarette test)				PASSED	
EN 1021-2:2006 (match test)				---	
LIGHTFASTNESS EN ISO 105-B02:1998 y EN ISO 105 B02/A01:2002 Colour degradation on blue sale (From 1 worst to 8 best)				>6	
COLOUR FASTNESS TO RUBBING EN ISO 105-X12:2002 Degradation and loss of colour on grey scale (From 1 worst to 5 best)			DRY	4-5	
			WET	4-5	
COLOUR FASTNESS TO DOMESTIC AMD COMERCIAL LAUNDERING (30°) EN ISO 105-C06:1997 Colour degradation on grey scale (From 1 worst to 5 best)				---	
DIMENSIONAL CHANGE IN DOMESTIC WASHING AND DRYING (%) EN ISO 3759:2008 – EN ISO 6330:2000 – EN ISO 5077:2008				-2%	-2%
SOILING AND CLEANABILITY FORD FLTM BN 112-08:2005 (From 1 worst to 5 best)				*4-5	
WATER REPELLENCY (HYDROPHOBIA) AATCC 79:2000 (value >300)				---	
OIL REPELLENCY (OLEOPHOBIA) EN ISO 14419:1999 – EN ISO 14419:1999/AC:2006 – AATCC 118:2002 (From 1 worst to 8 best)				---	
   					
NOTES: Repeat 27,9cm width x 16,4cm length +/-3.5% * Red & black felt-tipped pen 4-5 Coloured pencil 4-5 Grease 4 Orange juice 5 Synthetic soil 4 Red & blue pen 4 Crayon 4 Ketchup 4-5 Coffee 4-5 ATTENTION: WHEN CONFECTIONING OR WASHING THE SOFA COVER WITH VELCRO PLEASE ATTACH A PROTECTIVE CLOTH OR STRIP OVER THE VELCRO TO AVOID DAMAGE TO THE FABRIC.					